

Technical Data Sheet

Guaranteed Values

Universal Liner Brown Unsized

Brand:

OnegaFlex Brown Unsized

Parameters	Unit of measure	Test method	Substance (g/m ²)							
			42	45	50	60	65	70	80	90
Substance	g/m ²	ISO 536	42±1.5	45±1.5	50±1.5	60±1.5	65±1.5	70±2.5	80±2.5	90±2.5
Moisture	%	ISO 287	8.5 +/-1.5							
Bursting strength, min	kPa	ISO 2758	50	60	70	100	105	110	130	140
SCT _{cd} , min	kN/m	ISO 9895	0.40	0.45	0.50	0.75	0.80	0.90	1.00	1.10

Product description:

Universal liner that can be used for the production of packaging, as well as for the inner or face layers of corrugated board with a wide range of applications.

Information:

Test conditions:

Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Mill`s certificates

- ISO 9001