

## Technical Data Sheet

### Guaranteed Values

Fluting paper

Brand:

OnegaFlex

Parameters	Unit of measure	Test method	Substance (g/m <sup>2</sup> )							
			42	45	50	60	65	70	80	90
Substance	g/m <sup>2</sup>	ISO 536	42±1.5	45±1.5	50±1.5	60±1.5	65±1.5	70±2.5	80±2.5	90±2.5
Moisture	%	ISO 287	8.5 +/-1.5							
SCT <sub>cd</sub> , min	kN/m	ISO 9895	0.40	0.45	0.50	0.75	0.80	0.90	1.00	1.10
CMT <sub>30</sub> (sample width 15,0 mm), min	N	ISO 7263	-	-	-	55	65	70	90	110
CCT <sub>30</sub> , min	kN/m	GOST 28686	0.20	0.20	0.25	0.35	0.40	0.45	0.50	0.60

Product description:

Fluting paper for production corrugated board and packaging materials.

### Information:

#### Test conditions:

Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

#### Mill`s certificates

- ISO 9001