

Technical Data Sheet

Guaranteed Values

Newsprint standard

Brand:

KomiPress

Parameter	Unit	Test method	Substance		
			42	45	48.8
Basis weight	g/m ²	ISO 536	42.0 ± 1.5	45.0 +1.0/-1.5	48.8 +1.0/-2.0
Density, min	g/cm ³	ISO 534	0.6		
Smoothness, min	sec	ISO 5627	60		
Breaking length MD, min	km	ISO 1924-2	4.0	4.5	4.5
Opacity, min	%	ISO 2471	92	93	94
Moisture	%	ISO 287	7.5-9.5		
Brightness D65/10, min	%	ISO 2470	60		
Shade b			4.5-5.5		

Information:

Test conditions: Guaranteed values after conditioning measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Mill`s certificates

- ISO 9001
- ISO 14001
- ISO 45001

Manufacturer's Forest management system complies with extended level of NSFC standard (NSFC S+)

The system for verifying the legal origin of wood used in production complies with the requirements of the «Chain of custody of wood and wood-based products» international standard ISO 38200:2018 and the NSFC CoC standard

Product description:

Uncoated mechanical paper without recycled fiber.