

## Technical Data Sheet

### Guaranteed Values

Newsprint paper in reels

Brand:

OnegaPress

Parameters	Unit of measure	Test method	Substance (g/m <sup>2</sup> )						
			42	45	48.8	52	55	60	65
Substance	g/m <sup>2</sup>	ISO 536	42.0±1.5	45.0 +1.0 - 1.5	48.8 +1.0 - 2.0	52 ±1.5	55±1.5	60±1.5	65±1.5
Bulk	cm <sup>3</sup> /g	ISO 534	1.5-1.7						
Tear Strength CD, min	mN	ISO 1974	210						
Breaking Length MD, min	m	ISO 1924	4300	4500	4500	4500	4500	4500	4500
Bendtsen roughness, max	ml/min	ISO 8791-2	150			200			
Brightness, min	%	ISO 2470	60						
Opacity, min	%	ISO 2471	91	92	93	93	93	93	93
Moisture	%	ISO 287	7-10						

### Information:

#### Test conditions:

Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

#### Mill`s certificates

- ISO 9001

### Product description:

Onega press is designed for higt volume printing of popular editions: newspapers, leaflets and flyers, - containing text and monochrome or color illustrations on high speed presses. Paper is suitable for full color web offset printing, as well as for heat set web offset printing.