

Technical Data Sheet

Guaranteed Values

Printing paper bulky in reels

Brand:

OnegaText bulky

Parameters	Unit of measure	Test method	Substance (g/m²)								
			42	45	48.8	52	55	60	65	70	80
Substance	g/m²	ISO 536	42.0±1.5	45.0 +1.0 - 1.5	48.8 +1.0 - 2.0	52.0±1.5	55.0±1.5	60.0±1.5	65.0±1.5	70.0±2.5	80.0±2.5
Bulk	cm³/g	ISO 534	1.8 - 2.0								
Breaking Length MD, min	m	ISO 1924	4000								
Bendtsen roughness, max	ml/min	ISO 8791-2	800								
Brightness, min	%	ISO 2470	60								
Opacity, min	%	ISO 2471	91								
Moisture	%	ISO 287	7-10								

Information:

Test conditions:
Guaranteed values after conditioning,
measured at 50 ± 2% RH and 23 ±
1°C (ISO 187:1990)

Mill`s certificates
• ISO 9001

The timber used in production comply
with the basic requirements of NSFC
certification. The wood origin
verification process complies with the
requirements of the Russian chain of
custody standard STO NSFC.48861355-
004-2023 «National Forest Certification
System. Certification Requirements for
Chain of Custody Management»

Product description:

OnegaText is designed for monochrome and full color printing of books and magazines. Paper is suitable for web offset printing.