

Technical Data Sheet

Guaranteed Values

Brand:

Universal Liner Brown Unsized

OnegaFlex Brown Unsized

Parameters	Unit of measure	Test method	Substance (g/m ²)							
			42	45	50	60	65	70	80	90
Substance	g/m ²	ISO 536	42±1.5	45±1.5	50±1.5	60±1.5	65±1.5	70±2.5	80±2.5	90±2.5
Moisture	%	ISO 287	8.5 +/-1.5							
Bursting strength, min	kPa	ISO 2758	50	60	70	100	105	110	130	140
CMT ₃₀ , min	N	ISO 7263	-	-	35	55	65	70	90	110
SCT _{cd} , min	kN/m	ISO 9895	0.40	0.45	0.50	0.75	0.80	0.90	1.00	1.10

Product description:

Universal liner that can be used for the production of packaging, as well as for the inner or face layers of corrugated board with a wide range of applications.

Information:

Test conditions:
Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Mill`s certificates
• ISO 9001

The timber and recycled materials used in production comply with the basic requirements of NSFC certification. The wood origin verification process complies with the requirements of the Russian chain of custody standard STO NSFC.48861355-004-2023 «National Forest Certification System. Certification Requirements for Chain of Custody Management»