

Technical Data Sheet

Guaranteed Values

Printing paper in reels

Brand:

OnegaText

Parameters	Unit of measure	Test method	Substance (g/m²)								
			42	45	48.8	52	55	60	65	70	80
Substance	g/m²	ISO 536	42.0±1.5	45.0 +1.0 - 1.5	48.8 +1.0 - 2.0	52.0±1.5	55.0±1.5	60.0±1.5	65.0±1.5	70.0±2.5	80.0±2.5
Bulk	cm³/g	ISO 534	1.5 - 1.7								
Breaking Length MD, min	m	ISO 1924	4000								
Bendtsen roughness, max	ml/min	ISO 8791-2	150			200					
Brightness, min	%	ISO 2470	60								
Opacity, min	%	ISO 2471	91								
Moisture	%	ISO 287	7-10								

Information:

Test conditions:
Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Mill`s certificates
• ISO 9001

The timber used in production comply with the basic requirements of NSFC certification. The wood origin verification process complies with the requirements of the Russian chain of custody standard STO NSFC.48861355-004-2023 «National Forest Certification System. Certification Requirements for Chain of Custody Management»

Product description:

OnegaText is designed for monochrome and full color printing of books and magazines. Paper is suitable for web offset printing.