

Technical Data Sheet

Guaranteed Values

Universal Liner Brown Sized

Brand:

OnegaFlex Brown Sized

Parameters	Unit of measure	Test method	Substance (g/m ²)							
			42	45	50	60	65	70	80	90
Substance	g/m ²	ISO 536	42±1.5	45±1.5	50±1.5	60±1.5	65±1.5	70±2.5	80±2.5	90±2.5
Moisture	%	ISO 287	8.5 +/-1.5							
Bursting strength, min	kPa	ISO 2758	55	65	75	105	110	115	135	145
CMT ₃₀ , min	N	ISO 7263	-	-	40	60	70	75	95	115
SCT _{cd} , min	kN/m	ISO 9895	0.45	0.50	0.55	0.80	0.85	0.95	1.10	1.15
Cobb ₆₀ , max	g/m ²	ISO 535	70							

Information:

Test conditions:
Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Mill`s certificates
• ISO 9001

The timber and recycled materials used in production comply with the basic requirements of NSFC certification. The wood origin verification process complies with the requirements of the Russian chain of custody standard STO NSFC.48861355-004-2023 «National Forest Certification System. Certification Requirements for Chain of Custody Management»

Product description:

Universal liner that can be used for the production of packaging, as well as for the inner or face layers of corrugated board with a wide range of applications.