

Technical Data Sheet

Guaranteed Values

Offset paper (bulky)

Brand:

KomiOffset (bulky)

Parameter	Unit	Test method	Substance						
			65	70	80	90	100	120	160
Basis weight	g/m ²	ISO 536	65±2.0	70±2.5	80±3.0	90±3.5	100±4.0	120±5.0	160±5.0
Bulk	cm ³ /g	ISO 534	1.4-1.6						
Opacity, min	%	ISO 2471	84	85	87	88	91	91	91
Breaking length MD, min	km	ISO 1924	4.5	4.5	4.5	4.5	4.5	4.5	3.5
Roughness Bendtsen	ml/min	ISO 8791	250-800						
CIE whiteness	%	ISO 11475	142-148						
Brightness D65/10	%	ISO 2470	102-105						
Moisture	%	ISO 287	4.5-7						

Information:

Test conditions: Guaranteed values after conditioning measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Mill`s certificates

- ISO 9001
- ISO 14001
- ISO 45001

Manufacturer's Forest management system complies with extended level of NSFC standard (NSFC S+)

The system for verifying the legal origin of wood used in production complies with the requirements of the «Chain of custody of wood and wood-based products» international standard ISO 38200:2018 and the NSFC CoC standard

Product description:

Uncoated fine paper in reels and sheets for offset printing