

Technical Data Sheet

Guaranteed Values

Printing paper

Brand:

KomiText

Parameter	Unit	Test method	Substance
			45
Basis weight	g/m ²	ISO 536	45,0 +1,0/-1,5
Density	g/cm ³	ISO 534	min 0,60
Smoothness	sec	ISO 5627	80-200
Average breaking length, MD and CD	%	ISO 1924	min 2500
Moisture	%	ISO 287	7.0-9.0
Brightness D65/10, min	%	ISO 2470	min 65
Dirt spots 0.1-0.5 mm ²	%	GOST 13525.4	max 200

Information:

Test conditions: Guaranteed values after conditioning measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Mill`s certificates

- ISO 9001
- ISO 14001
- ISO 45001

Manufacturer's Forest management system complies with extended level of NSFC standard (NSFC S+)

The system for verifying the legal origin of wood used in production complies with the requirements of the «Chain of custody of wood and wood-based products» international standard ISO 38200:2018 and the NSFC CoC standard

Product description:

Uncoated mechanical paper without recycled fiber.