

Technical Data Sheet

Guaranteed Values

Brand:

Printing paper in reels, sized

OnegaText Sized

Parameters	Unit of measure	Test method	Substance (g/m ²)	
			70	80
Substance	g/m ²	ISO 536	70.0±2.5	80.0±2.5
Bulk	cm ³ /g	ISO 534	1.5 - 1.7	
Breaking Length MD, min	m	ISO 1924	4000	
Bendtsen roughness, max	ml/min	ISO 8791-2	200	
Brightness, min	%	ISO 2470	60	
Opacity, min	%	ISO 2471	91	
Cobb ₆₀ , max	g/m ²	ISO 535	50	
Moisture	%	ISO 287	7–10	

Product description:

OnegaText is designed for monochrome and full color printing of books and magazines. Paper is suitable for web offset printing.

Information:

Test conditions:

Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Mill`s certificates

- ISO 9001

The timber used in production comply with the basic requirements of NSFC certification. The wood origin verification process complies with the requirements of the Russian chain of custody standard STO NSFC.48861355-004-2023 «National Forest Certification System. Certification Requirements for Chain of Custody Management»