



Taiga Group LLC
Produced by: JSC "Syktyvkarskiy LPK" (JSC SLPK)
Syktyvkar, Russia



Technical Data Sheet

Guaranteed Values

White Kraft Paper Bulky

Brand:

KomiStar

Parameters	Unit of measure	Test method	Substance (g/m ²)			
			70	80	90	100
Substance tolerance	g/m ²	ISO 536	70±3	80±3	90±3	100±3
Moisture tolerance, min/max	%	ISO 287	5.0-8.0			
Bursting strength, min	kPa	ISO 2758	250	280	315	330
Tensile strength MD, min	kN/m	ISO 1924-3	5.3	6.0	6.8	7.3
Tensile strength CD, min	kN/m	ISO 1924-3	2.9	3.3	3.7	4.0
Air resistance (Gurley), min/max	sec	ISO 5636-5	20-70			
Cobb ₆₀ (top side), min/max	g/m ²	ISO 535	25-45			
Cobb ₆₀ (bottom side), min/max	g/m ²	ISO 535	25-45			
Brightness, min	%	ISO 2470	100			

Information:

Test conditions:

Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Mill`s certificates

- ISO 9001
- ISO 14001
- ISO 45001

Manufacturer's Forest management system complies with extended level of NSFC standard (NSFC S+)

The system for verifying the legal origin of wood used in production complies with the requirements of the «Chain of custody of wood and wood-based products» international standard ISO 38200:2018 and the NSFC CoC standard

Product description:

White Kraft Paper Bulky (with OBA) is made of bleached long fiber sulphate pulp and bleached short fiber sulphate pulp. For the production of carrier bags, consumer bags.