



Taiga Group LLC
Produced by: JSC "Syktyvkarskiy LPK" (JSC SLPK)
Syktyvkar, Russia



Technical Data Sheet

Guaranteed Values

White top kraftliner (WTKL)

Brand:

KomiWhite

Parameters	Unit of measure	Test method	Substance (g/m ²)						
			100	110	120	135	160	175	200
Substance tolerance	g/m ²	ISO 536	100±5	110±5	120±5	135±5	160±5	175±5	200±8
Moisture tolerance, min/max	%	ISO 287	7,5±1,5						
Bursting strength, min	kPa	ISO 2759	-	-	-	560	680	740	830
SCT _{CDr} min	kN/m	ISO 9895	1.80	2.05	2.25	2.60	3.10	3.30	3.70
Scott plybond, min	J/m ²	TAPPI 569	200						
Bendtsen roughness (top side), max	ml/min	ISO 8791-2	250	400			600		
Brightness (top side), min	%	ISO 2470	73						
Cobb ₆₀ (top side), max	g/m ²	ISO 535	35.0						
Cobb ₆₀ (bottom side), min/max	g/m ²	ISO 535	-	-	-	30,0-70,0			

Information:

Test conditions: Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Mill`s certificates

- ISO 9001
- ISO 14001
- ISO 45001

Manufacturer's Forest management system complies with extended level of NSFC standard (NSFC S+)

The system for verifying the legal origin of wood used in production complies with the requirements of the «Chain of custody of wood and wood-based products» international standard ISO 38200:2018 and the NSFC CoC standard

Product description:

Liner for corrugated board