

Technical Data Sheet

Guaranteed Values

Newsprint paper in reels

Brand:

OnegaPress

Parameters	Unit of measure	Test method	Substance (g/m ²)						
			42	45	48.8	52	55	60	65
Substance	g/m ²	ISO 536	42.0±1.5	45.0 +1.0 - 1.5	48.8 +1.0 - 2.0	52 ±1.5	55±1.5	60±1.5	65±1.5
Density	g/cm ³	ISO 534	0.55-0.65						
Tear Strength CD, min	mN	ISO 1974	210						
Breaking Length MD, min	m	ISO 1924	4300	4500	4500	4500	4500	4500	4500
Bendtsen roughness, max	ml/min	ISO 8791-2	150			200			
Brightness, min	%	ISO 2470	60						
Opacity, min	%	ISO 2471	91	92	93	93	93	93	93
Moisture	%	ISO 287	7-10						

Product description:

OnegaPress is designed for high volume printing of popular editions: newspapers, leaflets and flyers, - containing text and monochrome or color illustrations, on high speed presses. Paper is suitable for full color web offset printing, as well as for heat set web offset printing.

Information:

Test conditions:

Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Mill`s certificates

- ISO 9001

The timber used in production comply with the basic requirements of NSFC certification. The wood origin verification process complies with the requirements of the Russian chain of custody standard STO NSFC.48861355-004-2023 «National Forest Certification System. Certification Requirements for Chain of Custody Management»